

LISBON D IMOUT^(F/R)



TECHNICAL PROPERTIES

COMPOSITION	Polyester 100%	SOLAR REFLECTANCE	57.50%
WIDTH	2800mm	SOLAR ABSORPTANCE	42.3%
PACKING	40m / Roll	SOLAR TRANSMITTANCE	0.20%
THICKNESS	0.70mm (± 5%)	UV BLOCKING	UV_R:99.9%, UV_A:99.9%, UV_B:99.9%
WEIGHT	220.0g/sqm (± 5%)	UV PROTECTION FACTOR	50+, UV_A:0.1%, UV_B:0.1%
TENSILE STRENGTH	daN/50mm, Weft: 453.7	COLORFASTNESS GRAY SCALE	3.5
TEARING STRENGTH	daN, Warp: 0.7, Weft: 1.0	STRIPE SIZE	Solid 100mm, Sheer 70mm

CERTIFICATES



COLOR AVAILABILITY



FLAMMABILITY (NFPA 701 : 2015, METHOD 1)

SAMPLE NO.	WEIGHT(g)		WEIGHT LOSS (%)	AFTER FLAME TIME (s)	DRIP BURN (s)
	ORIGINAL	AFTER			
01	14.8	13.7	7.4	0	0
02	14.8	14.1	4.7	0	0
03	14.9	14.0	6.0	0	0
04	14.8	13.8	6.8	0	0
05	14.9	13.8	7.4	0	0
06	14.8	13.9	6.1	0	0
07	14.7	13.7	6.8	0	0
08	15.0	14.0	6.7	0	0
09	14.8	13.8	6.8	0	0
10	14.8	14.0	5.4	0	0
AVG	14.8	13.9	6.4	0	0

NOTE

- CONCLUSION : Based upon the results of the test report, the submitted sample meets the performance requirement as stated in NFPA 701 TEST METHOD 1 (2015)
- PERFORMANCE CRITERIA FOR TEST METHOD 1 (2015)
 DRIP BURN(s) _ AVG : LESS THAN 2 , WEIGHT LOSS(s) _ AVG : LESS THAN 40
 * No individual specimen's weight loss exceed the mean value plus 3 / Standard deviation 10.0



IMPORTANT

- Color sample may not necessarily be an exact match of the material to be used to produce your order. Return will not be accepted due to minor variations of color or textile.